

- 24 -

[CLAIMS]

1. A method of making a heat-sensitive lithographic printing plate precursor comprising the steps of
 - (i) providing a web of a lithographic support having a hydrophilic surface;
 - (ii) applying a coating comprising a phenolic resin on the hydrophilic surface of the web;
 - (iii) drying the coating;
 - (iv) a heating step wherein the web temperature is maintained above the glass transition temperature of the phenolic resin T_g during a period of between 0.1 and 60 seconds;
 - (v) an active cooling step wherein the web temperature is reduced at an average cooling rate which is higher than if the web would be kept under ambient conditions but not higher than 30°C/s ;
 - (vi) winding the precursor on a core or cutting the precursor into sheets.
2. A method according to claim 1 wherein the average cooling rate is not higher than 20°C/s .
3. A method according to claim 1 wherein the average cooling rate is not higher than 10°C/s .
4. A method according to any preceding claim wherein at the beginning of the cooling step the web temperature is higher than T_g and wherein during the cooling step the web temperature is reduced from T_1 to T_2 , T_1 being higher than T_g and T_2 being lower than T_g , at an average cooling rate which is lower than 10°C/s .
5. A method according to claim 4 wherein during the cooling step the web temperature is reduced
 - in a first phase down to T_1 at an average cooling rate of at least 10°C/s ; and
 - in a second phase from T_1 to T_2 at an average cooling rate which is lower than 10°C/s .

- 25 -

6. A method according to claim 4 wherein during the cooling step the web temperature is reduced
 - in a first phase down to T1 at an average cooling rate of at least 10°C/s; and
 - 5 - in a second phase from T1 to T2 at an average cooling rate which is lower than 10°C/s; and
 - in a third phase from T2 to about ambient temperature at an average cooling rate of at least 10°C/s.
7. A method according to claim 4, 5, or 6 wherein the cooling from
10 T1 to T2 proceeds at an average cooling rate which is lower than 5°C/s.
8. A method according to any of claims 4 to 7 wherein T1 is Tg+20°C and T2 is Tg-20°C.
9. A method according to any of claims 4 to 7 wherein T1 is Tg+10°C
15 and T2 is Tg-10°C.
10. A method according to any of the previous claims wherein the heating step is carried out by blowing hot air or steam onto the precursor or by exposing the precursor to infrared or microwave radiation.